



WHITEFINE NR



**MEDIUM WEAR
SHEETING
WHITE FOOD
QUALITY**

FEATURES

Wear resistant natural rubber, white, food grade, meeting regulation (EC) 2023/2006 (European legislation) and FDA classification (American legislation).

REGULATIONS

- Meeting european regulations (EC) 2023/2006
- The material is in compliance with FDA 21 CFR Part. 177. Indirect Food Additives: Polymers. Sec 177.2600 Rubber articles intended for repeated use for contact with aqueous food
- Quality certificate available under request

APPLICATIONS

Hoppers, chutes, operating cyclones, vibrating lines, silos, etc., linings to protect equipment against very abrasive fine grain size products wear, due to their very nature (rock, wood, metal, all fine particle size materials, chemical products, etc.), density and hardness (medium to high), forms (fine particles, bulks), with dry conditions and maximum temperature +70°C.
Hanging panels fostering materials cleaning and removal.
Areas of activity: sand and gravel quarries, aggregate and cement industries, concrete plants, food processing industries, etc.

ADVANTAGES

- Excellent mechanical properties: tensile strength, elongation at break, tear resistance, abrasion, etc.
- Excellent resistance to fine grain size products projection and fretting wear: sand, shot blasting, fine particles, abrasive dust, etc.
- Corrosion protection
- Noise and vibration propagation reduction
- Possibility to be produced with bonding layer for cold vulcanizing or with steel backing for mechanical fixing

BENEFITS

- Performance
- Legality
- Food safety
- Hygiene, cleanliness
- Service life

MAINTENANCE RECOMMENDATION

Always follow manufacturer warnings and instructions when using any cleaning product.

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

Measured characteristics		Standard	Value	
MECHANICAL				
Rubber compound - white			NR	R320
Density			1.00 ±0.05	g/cm³
Hardness	ASTM D2240		40 ±5	Shore A
Tensile strength	ISO 37		≥20	MPa
Elongation at break	ISO 37		≥600	%
Tear resistance	ISO 34-1		≥32	N/mm
Abrasion resistance (5N)	ISO 4649		≤80	mm³
Compression set after 22h at 70 °C	ISO 815-1		≤25	%

TEMPERATURE

Working temperature		-40/+85	°C
---------------------	--	---------	----

AGEING

Δ Hardness after 168h at 70 °C	ASTM D573	≤5	Shore A
Δ Tensile strength after 168h at 70 °C	ASTM D573	≥ -15	%
Δ Elongation at break after 168h at 70 °C	ASTM D573	≥ -20	%


CHEMICAL RESISTANCE

Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons
Good	Medium	Medium	Non suitable

IDENTIFICATION

Branding	Without.
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.
Wrapping	White polyethylene film.
Labelling	Self-adhesive label indicating product name, dimensions, area in m², nominal weight, and product code to allow product traceability.

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

NR	MEDIUM WEAR SHEETING	WHITEFINE			
THICKNESS mm	WIDTH mm	LENGTH m	WEIGHT kg/m ²	SIDES FINISH	
2±0.3	1400±2 %	15±2 %	2.01	2 SIDES MATT	
3±0.3	1400±2 %	10±2 %	3.01	2 SIDES MATT	
4±0.4	1400±2 %	10±2 %	4.01	2 SIDES MATT	
5±0.4	1500±2 %	6±2 %	5.01	2 SIDES MATT	
6±0.5	1500±2 %	6±2 %	5.82	2 SIDES MATT	
8±0.7	1500±2 %	6±2 %	8.02	2 SIDES MATT	
10±1.0	1500±2 %	6±2 %	10.03	2 SIDES MATT	
12±1.0	1500±2 %	6±2 %	12.03	2 SIDES MATT	

