

# BLACKFIRE CR





## SPECIAL WEAR SHEETING FIRE RESISTANT

#### **FEATURES**

Fire and wear resistant high grade chloroprene.

#### REGULATIONS

- Fire resistant classified M2 following UNE 23727
- NF F 16101: smoke opacity following NF X 10702 and toxicity of emitted gases following NF X 70100, class F5

#### **APPLICATIONS**

General equipment protection or other applications subject to risk of fire.

#### **ADVANTAGES**

- Very good fire resistance
- Very good wear resistance
- Excellent ageing resistance
- Very good heat resistance
- Antistatic
- Very good resistance to animal or vegetable oils
- Matte finish to guarantee a good surface finished quality, to secure an easy unrolling, and to facilitate adhesive bonding processes
- Possibility to be produced with bonding layer for cold vulcanizing or with steel backing for mechanical fixing

### **BENEFITS**

- Performance
- Service life
- Safety

#### **MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES**

	Measured characteristics	Standard	Value			
MECHANICAL						
	Rubber compound - black		CR C738			
	Density		1.47 ±0.05	g/cm³		
	Hardness	ASTM D2240	70 ±5	Shore A		
	Tensile strength	ISO 37	≥10	MPa		
	ISO 37	≥250	%			
	ISO 34-1	≥20	N/mm			
	ISO 4649	≤200	mm³			
Comp	ISO 815-1	≤20	%			
TEMPERATURE						
	Working temperature		-30/+120	°C		
AGEING						
2	ASTM D573	≤5	Shore A			
ΔTens	ASTM D573	≤-15	%			
Δ Elongation	ASTM D573	≤-25	%			
OIL RESISTANCE						
Oil IRM 901	ISO 1817	≤10	%			
Oil IRM 903	ISO 1817	≤55	%			
CHEMICAL RESISTANCE						
Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hyd	drocarbons		
Good	Medium	Very good	Medium			
IDENTIFICATION						
Branding	Without.					
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.					
Wrapping	Black polyethylene film.					
Labelling	Self-adhesive label indicating product name, dimensions, area in m², nominal weight, and product code to allow product traceability.					

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

CR	SPECIAL WEAR SHEETING	BLACKFIRE		
THICKNESS	WIDTH mm	LENGTH m	WEIGHT kg/m²	SIDES FINISH
3±0.3	1400 ± 2 %	10 ± 2 %	4.41	2 SIDES MATT
4±0.4	1400 ± 2 %	10 ± 2 %	5.88	2 SIDES MATT
5±0.4	1400 ± 2 %	10 ± 2 %	7.35	1 SIDE SMOOTH/1 SIDE MATT
6±0.5	1400 ± 2 %	10 ± 2 %	8.82	1 SIDE SMOOTH/1 SIDE MATT
8±0.7	1400 ± 2 %	10 ± 2 %	11.76	1 SIDE SMOOTH/1 SIDE MATT
10 ±1.0	1400 ± 2 %	10 ± 2 %	14.7	1 SIDE SMOOTH/1 SIDE MATT

